

## FASSON® Vellum PiggyBack

Issued July 2024

**Introduction**

A self-adhesive paper sheet product for offset printing.

The construction consists of a white woodfree face paper and two self-adhesive layers and backing papers.

**Description**

Face: A premium-quality uncoated woodfree, machine-calandered paper.  
This product, FSC® C011032 certified, is sold as FSC® Mix Credit.

## Availability

<i>Backing</i> 	<i>Adhesive</i> 	Permanent
	No cracklines	

**Printing & Conversion**

Offset printing.

Before applying the label, the surface must be clean, dry and grease-free.

**Recommendations for use**

Functional or decorative label applications where a second self-adhesive label is needed when the first layer has been peeled off or applied. E.g. labels on consumer goods and direct mail.

For indoor use.

**General**

Shelf life: 2 years stored at 20°C / 55% R.H.

Total caliper ( $\pm 10\%$ ): 265 micron

For information regarding EHS regulation, please visit our website under downloads “Technical bulletins“ TB 7.8 Product Compliance Fasson Offset” and for technical guidance “Technical bulletins“ – Offset printing.

## PRODUCT CHARACTERISTICS

### Physical properties

#### Face

Basis weight:	80 g/m <sup>2</sup>	ISO 536
Caliper:	76 micron	ISO 534
Opacity:	91 %	ISO 2471

#### Adhesive

Permanent: General-purpose water-based permanent adhesive with a high initial tack and high adhesion on most common substrates.

#### Permanent

Adhesion (N/25mm) (FTM 1 on steel/20 min. bond time)	15.4
Tack (N) (FTM 9 on st.steel)	10.3
Minimum application temperature	+5
Service temperature range after 24 hrs (°C)	+80
Resistance to cold (°C) <sup>1)</sup> down to	-20

<sup>1)</sup> Not fully resistant until after adhesion reaches full strength – after at least 24 hrs.

#### Backing

No cracklines: A bleached one side-coated white kraft, especially designed for sheet products, featuring minimal moisture sensitivity.

Basis weight:	80 g/m <sup>2</sup>	ISO 536
Caliper:	81 micron	ISO 534

This product, FSC® C011032 certified, is sold as FSC® Mix Credit.

#### Guarantee and liability:

All product statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. Products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.  
All products are sold subject to Torraspapel – Lecta's general terms and conditions of sale, see <https://www.lecta.com/terms>  
Fasson® and Crack-Back® are registered trademarks of Avery Dennison Corporation and related entities, and the products are produced by Torraspapel - Lecta under license from Avery Dennison Corporation and related entities for EMENA only.